


## FAVETON ORONA TECHNICAL CHARACTERISTICS

FAVETON FORMATS	FAVETON ORONA
SIZES	250 x 60 x UP TO 1500 mm
INTERIOR SIZES	44 mm



TECHNICAL PROPERTIES	FAVETON ORONA VALUES
LINEAL THERMAL EXPANSION ISO 10545-8	EXPANSION COEFFICIENT $5,7 \times 10^{-6}$ (K <sup>-1</sup> ). ITC TEST
THERMAL SHOCK RESISTANCE ISO 10545-9	ACCORDING TO TEST UP TO 145° UNALTERABLE
MOISTURE EXPANSION ISO 10545-10	AVERAGE VALUE < 0,1mm/m, MAXIMUM VALUE < 0,1 mm/m. ITC TEST
CHEMICAL RESISTANCE ISO 10545-13	ONLY APPLICABLE IN CORROSIVE CONDITIONS. MINIMUM CLASS G AND B
STAIN RESISTANCE ISO 10545-14	MINIMUM CLASS 3
COLOR DIFFERENCES ISO 10545-16	$\Delta E < 2$